



«ООО БИТ»
КАРТОН И БУМАГА

197343, г.Санкт-Петербург, ул. Матроса Железняка, д.57, лит.А
+7 (812) 468-33-33 bit929@mail.ru

109052, г.Москва, ул.Смирновская, дом 19.
+7 (495) 789-80-34 bit945@mail.ru
<https://bit-karton.ru>

Allyking Cream, GC2

Производитель:

Asia Pulp & Paper



Описание:

Целлюлозный упаковочный картон с двукратным мелованием лицевой стороны и светло-кремовым оборотом.

Область применения:

Производство высококачественной красочной упаковки для пищевой и фармацевтической продукции, подарочной упаковки, упаковки для косметики и парфюмерии и т.д.

Диапазон граматур:

200-350 г/м²

Техническая спецификация

Technical Information	Unit	Margin	Specification										Standards
Basis Weight	g/m ²	±3%	200	215	220	235	240	250	270	295	325	350	ISO 536
	24"x36" 500 (lb)		123	132	135	144	147	154	166	181	200	215	
Thickness	µm	±3%	325	350	360	385	395	420	460	510	560	610	ISO 534
	pt		12.8	13.8	14.2	15.2	15.6	16.5	18.1	20.1	22.0	24.0	
Taber Stiffness	mN•m	target	3.95	5.32	5.68	7.05	7.57	8.31	10.8	15.2	17.8	24.5	ISO 2493
		min	3.36	4.52	4.83	5.99	6.43	7.06	9.18	12.9	15.1	20.8	
Taber Stiffness	mN•m	target	8.18	9.48	11.3	12.6	13.2	15.8	20.9	29.3	32.2	40.0	

Technical Information	Unit	Margin	Specification								Standards
min	6.95	8.06	9.61	10.7	11.2	13.4	17.8	24.9	27.4	34.0	
Moisture	%	±1.0	7.0								ISO 287
PPS PPS Roughness-top	µm	≤	1.70								ISO 8791-4
Brightness D65/10 - top	%	±2.0	82.0								ISO 2470-2
Gloss-top	%	±5	40.0								TAPPI 480
IGT IGT Picking-top	m/s	≥	1.20								ISO 8254-1
Cobb 180s -	g/m ²	≤	60.0								ISO 535
Scott Plybonding	J/m ²	≥	130								TAPPI 569
Squareness	mm	≤	2.0								GB/T 451.1
Size Deviation	mm	≤	2.0								
Optical Brightening Agent	---	---	Negative								GB 31604.47
Food Safety Standad	As per GB4806.8-2016"National food safety standards,food contact paper and paperboard materials and products"										
Test climate 23°C/50%RH□according to ISO 187□											

<https://bit-karton.ru/product/ALLYKING-CREAM/>